## **Chemical reliability of RESITRIX**



Inorganic substances				
Acids and bases:				
Ammoniakum	strength	+		
Benzo acid	_	+		
Butyric acid		Δ		
Fluoric acid		Δ		
Tannin acid		+		
Potassium hydroxide		+		
Limewash	satturated	+		
Soda lye	< 25%	+		
Nitric acid	< 10%	+		
Muriatic acid	< 11%	+		
Sulfuric acid	<15%	+		
<b>Aqueous solution:</b>				
Ammoniakum water		+		
Ammoniakum carbonate		+		
Ammoniakum nitrate		+		
Cast		+		
Potssium bromide	satturated	+		
Lime		+		
Copper sulfate		+		
Magnesium chloride		+		
Soda (ash)		+		
Sodium chloride	satturated	+		
Natrium sulfate		+		
Natrium sulfite		+		
Water		+		
Hydrogen peroxide	strenght	Δ		
Salts:				
Prickly salt		+		
Nitrates		+		
Phosphates		+		
Sulfates		+		

Organic substances		
Aliphatic compound	ds:	
Acetone		Δ
Acrylic acid	< 99%	+
Formic acid	< 88%	+
Ethanol		+
Ethyl alcohol		+
Boracic acid	3%	+
Cyclohexane		+
Acetic acid	< 20%	+
Formaldehyde		+
Glycerin		+
Glykol		+
Methyl alcohol	100%	+
Methylene chloride		+
Lactic acid	< 8%	+
Tannin acid		+
Oxalic acid		+
Phenolics		Δ
Tartaric acid		+
Citric acid		•
Aromatic compound	ds:	
Benzine		Δ
Benzene		Δ
Petroleum		Δ
Tetralin		Δ
Toluol		Δ
Xylene		Δ
Sundries:		
Bleach		•
Diesel oil		Δ
Gear oil		Δ
Glycerin		+
Heating oil		Δ
Sewage		+
Kerosene		$\Delta$
Ketone		Δ
Motor oil		Λ
Gasoline		Λ
Lube oil		Λ
Soap solution		
Silicone oil		+
Nutritional oil		
Bird excrements		•
		+
Detergent Cement		+
Cement		+

Legend:	
limited resistant	•
resistant	+
volatile	Δ